

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problems Mailbox.**

⑫

**EUROPEAN PATENT APPLICATION**

⑮ Application number: 88309542.4

⑮ Int. Cl. 4: **B29C 61/00 , C08J 5/18 ,**  
**//B29K27/18**

⑯ Date of filing: 12.10.88

⑰ Priority: 19.10.87 US 110145  
23.09.88 US 248887

⑱ Date of publication of application:  
26.04.89 Bulletin 89/17

⑲ Designated Contracting States:  
AT BE CH DE ES FR GB GR IT LI LU NL SE

⑴ Applicant: W.L. GORE & ASSOCIATES, INC.  
555 Paper Mill Road P.O. Box 9206  
Newark Delaware 19714(US)

⑵ Inventor: House, Wayne D.  
Rt. 4 Box 948  
Flagstaff AZ 86001(US)  
Inventor: Myers, David J.  
HC75 Box 2476  
Camp Verde, AZ 86322(US)

⑶ Representative: Taylor, Derek George et al  
Mathisen, Macara & Co. The Coach House  
6-8 Swakeleys Road  
Ickenham Uxbridge UB10 8BZ(GB)

⑷ **Rapid recoverable PTFE and a process for its manufacture.**

⑸ This invention relates to porous polytetrafluoroethylene (PTFE) materials having the property of rapid recovery and a process for producing these materials. The microstructure of the porous PTFE material consists of nodes interconnected by fibrils, substantially all of the fibrils having a bent or wavy appearance.

The process comprises extruding a billet of a mixture of coagulated dispersion of PTFE and liquid lubricant, removing the lubricant, stretching the material longitudinally and maintaining it at a temperature between 35°C and the crystalline melt point during stretching, compressing the PTFE in the direction of fibrils to reduce its size, restraining the PTFE in its compressed state, and heating the compressed PTFE.

**EP 0 313 263 A2**

## RAPID RECOVERABLE PTFE AND A PROCESS FOR ITS MANUFACTURE

This invention relates to porous polytetrafluoroethylene (hereinafter PTFE) materials having the property of rapid recovery and a method for producing these materials. Recovery, in the context of this specification, refers to recovery from deformation, in particular stretching. The microstructure of the porous PTFE material consists of nodes interconnected by fibrils, substantially all of the fibrils having a bent or wavy appearance.

Articles made from these materials are particularly suitable for use in the medical field, but are also useful in other areas such as filtration and fabric applications.

Strong, porous PTFE products and their method of manufacture were first described in U.S. Patent 3,953,566. Such products have found widespread acceptance in many fields. They are used in the medical field as replacement veins and arteries, as patch materials, as sutures and as ligaments. They have also found use in the fields of waterproof and breathable clothing, filtration, sealants and packings, and in threads and filaments for weaving and sewing. These products possess a microstructure of nodes interconnected by fibrils.

U.S. Patent 4,443,511 discloses a method of making a laminated fabric composed partly of porous PTFE that has improved elastic properties. This patent, however, only discloses how to make a stretchable laminated article but does not teach how to provide porous PTFE with the property of rapid recoverability.

According to the present invention there is provided a porous shaped article consisting essentially of PTFE, said article having a microstructure of nodes interconnected by fibrils, said article having a rapid recovery of more than about 5.5%.

The present invention also provides an extruded, expanded article, heat treated above its crystalline melt point made of a material consisting essentially of polytetrafluoroethylene (PTFE), said porous PTFE having been subsequently compressed at least 50% in the direction in which rapid recoverable characteristics are desired, restrained and heated.

The products of this invention are preferably made by taking shaped articles of porous PTFE which have been expanded by stretching and have been heated above their crystalline melt point, compressing these articles in a direction parallel to but opposite to that in which they were expanded by stretching, restraining the articles and heating them at a temperature above their crystalline melt point for a period of time, allowing them to cool, removing the restraint and restretching them in the direction of original stretch to approximately their original length.

This invention will now be particularly described, by way of example, with reference to the accompanying drawings in which:-

Figure 1 is a schematic representation of the microstructure of porous PTFE known in the prior art;

Figure 2 is a schematic representation of the microstructure of the PTFE material of the present invention;

Figure 3 is a photomicrograph (taken at 500x magnification) of the surface of prior art PTFE material made in accordance with U.S. Patent No. 3,953,566 that was stretched in one direction;

Figure 4 is a photomicrograph (taken at 500x magnification) of the surface of PTFE material of the present invention;

Figure 5 is a photomicrograph (taken at 20x magnification) of the wall cross section of the PTFE material of the prior art;

Figure 6 is a photomicrograph (taken at 20x) of the wall cross section of the PTFE material made in accordance with the present invention;

Figure 7 is a schematic diagram of a compression procedure for Example 4;

Figures 8 and 9 are photomicrographs (taken at 500X) of the wall cross-section of the PTFE material of the prior art, and

Figures 10, 11, 12 and 13 are photomicrographs (taken at 500X) of the wall cross-section of the PTFE material described in Example 1, Table 1, samples 1, 2 and 3, and 4 respectively.

A method for producing porous PTFE products having a desirable rapid recovery property is provided. The porous products produced according to the invention are distinct from prior porous PTFE products in that they possess a rapid recovery property of greater than about 5.5%, i.e. they have a spring-like property. Furthermore, articles made by the present invention may undergo repeated applications of tensile loads and demonstrate approximately the same rapid recovery after each successive load application and removal cycle.

Rapid recovery as herein defined is the difference between the extended length of the material and the recovered length with respect to the recovered length. The extended length is the length of material under

tensile load and recovered length is the length of material measured 5 seconds after release of the tensile load.

An advantage possessed by rapid recoverable PTFE tubes made according to this invention is the improved bending characteristics demonstrated over the previous porous PTFE tubes. These tubes also show improved resistance to kinking, constriction or collapse under flexure.

The porous PTFE material that provides the precursor for this invention may be produced by the method described in U.S. Patent No. 3,953,566. Using this method, a liquid lubricant is mixed with a commercially available powder of PTFE, and the mixture is extruded by a ram-type extruder or other type of extruder. The material is then expanded by rapid stretching either uniaxially, biaxially, or multiaxially after the liquid lubricant is removed from it.

The material after stretching is then heated while restrained to a temperature above the crystalline melt point of the polymer and held there for a period of time. The time and temperature will vary depending on the amount of material being heated. In general, the higher the temperature used, the shorter the time. A strong porous material is produced. This material having undergone uniaxial expansion has a microstructure of nodes interconnected by fibrils that are essentially parallel and straight.

While this invention can be used with products that have been biaxially or multi-axially stretched, the description that follows will describe a uniaxially stretched article.

Figure 1 is a schematic plan view of a section of a uniaxially expanded PTFE material produced using the techniques disclosed in the 3,953,566 patent. This section as seen under a microscope is depicted as possessing many nodes interconnected by many fibrils. This shows the microstructure in which the longitudinal axes of the fibrils are all substantially parallel to the direction of expansion.

This precursor material is compressed in the direction parallel to but opposite to the direction in which it was originally expanded by stretching. The amount of compression depends on the nature of the shaped article and the desired product. In one embodiment the shaped article is compressed up to the point just prior to when it starts to become wrinkled or crimped. In this embodiment the shaped article is compressed to less than about one half of its original length and preferably to less than about one quarter of its original length. A second embodiment continues the compression such that wringles or crimps are intentionally created. In a third embodiment, the shaped article may be compressed to a lesser extent so that it is less than its original length but greater than half of its original length. In this third case the rapid recovery characteristic is greater than that of the precursor article, however, less than that for a more compressed article.

The percent compression is calculated from the following equation:

$$C\% = \frac{[l_0 - l_c]}{l_0} \times 100\%$$

where  $l_0$  is the original length of the precursor material and  $l_c$  is the compressed length.

The material is then restrained in its compressed state and heated in an oven at an oven temperature in the range of 100° to 400° C with the most preferred oven temperature being about 380° C. The heating may be done in a variety of types of ovens. The period of time during which the compressed article is heated may vary, but in any event, the lower the temperature, the longer time the article must be restrained. The time required for heating also may vary depending on oven temperature, type of oven, and mass of the material.

While it is preferable to utilize a heating step, the material exhibits the rapid recovery characteristic if it is compressed and restrained at room temperatures, but it must be restrained for long periods of time, at least several days.

After the compressed material has been heated, it is cooled thereby to about 23° C. Cooling may occur through natural air currents, or by forced cooling.

After cooling, the restraint is removed. Removal of the restraint prior to cooling of the compressed porous PTFE article may cause the article to lose some rapid recovery characteristics. The material is then restretched in the direction of original stretch to approximately its original length.

While the foregoing has described the starting material for this invention as porous PTFE materials which have been heated above their crystalline melt point, porous PTFE materials which have not been so heated may also be used. These materials, however, do not demonstrate the range of rapid recovery found in heat treated materials but they do demonstrate rapid recovery greater than that exhibited by precursor PTFE materials.

PTFE fibrils of any length in the article of this invention demonstrate the rapid recovery phenomenon; preferably, however, the fibrils in the article of this invention have an average length of less than 100  $\mu$ .

The porous PTFE with rapid recovery is best understood by reference to the drawings provided. Figure 2 is a schematic plan view of a section of expanded PTFE made according to this invention as seen under a microscope. Therein, nodes 12 are interconnected by fibrils 14. It is clearly seen that unlike the fibrils in Figure 1, substantially all of the fibrils in Figure 2 have a bent or wavy appearance. Figure 3 and 4 are photomicrographs of PTFE materials made in accordance with the teachings of the prior art and that made in accordance with present invention respectively. Figure 3 is a photomicrograph of the precursor tube that was subsequently compressed, restrained, heat treated and restretched in the direction of original stretch to approximately its marginal length, as shown in Figure 4.

Although the microstructure, specifically substantially all of the fibrils, undergoes a change in appearance, the overall appearance to the naked eye remains substantially unchanged. Figure 5 is a photomicrograph of the wall cross section of the precursor PTFE tube material. Figure 6 is a photomicrograph of the wall cross section of the PTFE tube material processed in accordance with the steps of this invention. That product shows smooth surfaces similar to those found in the precursor materials. One embodiment of the present invention is where the macrostructure (external surfaces and for a tube, external and internal surfaces) of the material does not demonstrate any apparent visible change in appearance. In an alternative embodiment the exterior surface, and/or interior surfaces of the PTFE material can be modified to produce a corrugated or rough surface.

Finished products made according to the method of this invention may include articles such as films, membranes, sheets, tubes, rods, and filaments. Sheets may also be made by slitting tubes longitudinally.

Porous rapid recoverable materials, including tubes, films, membranes, or sheets, maintain their hydrophobic nature and are also permeable to water vapour, causing them to be waterproof and breathable. They may be laminated, impregnated, and bonded to other materials and fabrics to provide composite structures having rapid recovery properties in addition to the known properties attributed to expanded PTFE. These rapidly recoverable PTFE articles are useful in the medical field in applications such as vascular grafts, in fabric applications, as well as in filtration areas.

An Instron tensile tester was used for all testing. All tests were performed at a temperature of  $23^{\circ}\text{C} \pm 2^{\circ}\text{C}$ . Each sample was cut in half transversely so that one part could be used to determine the maximum tensile force and the other to determine the rapid recovery. A crosshead speed of 500 mm/min and initial grip separation of 150 mm was used for all tests.

For samples that are too small to accommodate the 150 mm grip separation and allow enough material within the grips to prevent slippage of the sample within the grips, other combinations of crosshead speed and grip separation may be used provided the ratio of crosshead speed to initial grip separation is equal to 3.33 minutes<sup>-1</sup>. By maintaining the ratio of crosshead speed to initial grip separation constant, all tensile tests are performed at a strain rate of 333%/minute.

First the maximum tensile force of one half of the sample material was determined. This was done on the Instron tester using standard pneumatically actuated cord grips. Sample breaks occurred away from the edge of the grips. The maximum tensile force was measured for tubes, rods and sheets per the examples. For the sheet example, the sheet was folded in half longitudinally and placed between the cord grips.

To apply 1% of the maximum tensile force, the cord grip were removed and replaced with pneumatically actuated flat rubber-faced grips. The other half of the sample (in either tube or rod form, or unfolded sheet, per the examples) was placed between these grips and a tensile load of 1% of the previously determined break force or maximum tensile force was applied using identical grip separation and strain rate as described above.

The length ( $l_r$ ) of the sample while under the 1% of maximum tensile force was determined as the distance of the grip separation. Alternatively, length ( $l_r$ ) may be measured from the Instron tester's chart recorder.

Immediately after reaching a tensile load equivalent to 1% of the maximum tensile force, the lower Instron grip was quickly released in order to allow the sample to recover. Five seconds after the release of tension, the actual length ( $l_r$ ) of the sample that had been between the grips of the tester was measured.

The percent rapid recovery was then calculated from the following equation:

$$R.R\% = \frac{(l_r - l_r)}{l_r} \times 100\%$$

where  $l_t$  was the test sample length under tensile load and  $l_r$  was the test sample length measured 5 seconds after release of tensile load.

Wall thickness measurements of the precursor tubes were taken by cutting a 2.5cm long sample from the end of the tube sample with a razor blade. This sample was then smoothly fitted over a stainless steel mandrel of outside diameter corresponding to the inside diameter of the tube. The thickness measurement was made using a profile projector to measure the distance from the outer surface of the mandrel to the outer surface of the cut end of the tube sample. Measurements were made at three places spaced approximately 120° apart around the circumference of the tube. The wall thickness of the sample was taken as the mean of these three measurements.

The fibril length of the test samples in the examples following was determined by photographing the surface of the sample under 200x magnification. Two parallel lines were drawn 12mm above and below the longitudinal centerline of the photographs, parallel to the direction of the fibrils. Following the top edge of the upper line and starting from the left margin of the photograph, the distance from the right edge of the first distinct node to the left edge of the second distinct node was measured as the first fibril length. Measurements were made using dividers referenced to a scale that accounted for the magnification factor.

Five consecutive fibril length measurements were made in this manner along the drawn line. The photograph was rotated 180° and five consecutive fibril length measurements were taken from the left margin of the photograph along the top edge of the second drawn line. The mean fibril length of the sample was taken to be the mean of the ten photograph measurements.

Both wall thickness and fibril length measurements were made on the precursor tubes prior to the inventive steps being applied.

The following examples which disclose processes and products according to the present invention are illustrative only and not intended to limit the scope of the present invention in any way.

## EXAMPLE 1

### RAPIDLY RECOVERABLE EXPANDED PTFE TUBES

CD123 fine powder PTFE resin (obtained from ICI Americas) was blended with 150cm<sup>3</sup> of ISOPAR M (Trade Mark), odorless solvent (obtained from the Exxon Corporation), per pound of PTFE resin. The mixture was compressed into a tubular billet, heated to about 60°C and extruded into tubes in a ram extruder having a reduction ratio of about 240:1. Lubricant was removed from the extrudate by drying in a forced convection air oven at 250°C for thirty minutes. The tubes were then expanded by stretching utilizing the stretching technology taught in U.S. Patent 3,953,566. Sample tubes 1,2,3 and 5 in Table 1 were expanded 8.4:1, at a rate of about 50% per second in a forced convection air oven at a temperature of 290°C. These tubes had fibril lengths of about 35 microns. Sample tubes 4 were expanded 2.3:1, at a rate of about 160% per second in a forced convection air oven at a temperature of 290°C. These tubes had a fibril lengths of about 10 microns. All tubes, except sample 5, were subsequently heat treated in a gravity convection air oven for 90 seconds at 393°C. All tubes had a 10mm inside diameter.

One tube of each type was retained as a control sample. Percent rapid recovery measurements for the control or precursor tube are shown in comparison to tubes processed with the method of this invention in Table 1.

Tubes were fitted over stainless steel mandrels of 10mm outside diameter. One end of each tube was secured to its mandrel with a restraining wire. The free end of each tube sample was pushed by hand longitudinally toward the restrained end of the tube, thus compressing the tube sample longitudinally. The percentages of compression for each sample were calculated with the formula described above and are presented in Table 1. Each tube sample was compressed uniformly without wrinkling or otherwise distorting the exterior surface. The free end of each tube was secured to the mandrel with a second restraining wire. Each tube and mandrel assembly was placed in a gravity convection air oven for a predetermined time and oven temperature, both parameters of which are presented in Table 1. Each tube and mandrel assembly was removed from the oven and allowed to cool to about 23°C. The restraining wires for each assembly were removed and the tubes were removed from their mandrels. Each sample was restretched in the direction of original stretch to approximately its original length and allowed to recover for at least one hour. Percent rapid recovery was calculated for each tube using the equation previously described. Results of the

percent rapid recovery are summarized in Table 1.

5

10

15

20

25

30

35

40

45

50

55

Table 1  
RAPID RECOVER TUBES

RAPID RECOVER TUBES										
Sample	Precursor Tube Characteristics (Control)					Inventive Process Parameters			Inventive Tube Rapid Recovery Characteristics	
	Wall Thickness (mm)	Mean Fibril Length Micron	Prior Heat Treatment to above crys melt point	1% of Max Tensile Force (kg)	% Rapid Recovery	% Compression	Oven Temp ° C	Time Heated (min)	1% of Max Tensile Force (kg)	% Rapid Recovery
1	.0	29	Yes	.66	3.8	84	380	3	.53	22.3
2	1.0	32	Yes	.63	3.7	50	380	3	.57	5.7
3	1.2	39	Yes	.69	1.2	85	100	3000	.63	16.9
4.	1.1	10	Yes	.88	3.3	66	380	3	.68	19.5
5.	.7	31	No	.38	3.2	72	300	10	.28	5.8



## EXAMPLE 2

5

RODS

10 A rod of one quarter-inch (0.635 cm) nominal diameter GORE-TEX (Trade Mark) Joint Sealant, available commercially from W. L. Gore and Associates, Inc., Elkton, MD, was used as the precursor porous PTFE material to be processed by the method of this invention. This material had not been heated above its crystalline melt point.

15 A portion of the test sample was cut off and retained as a control for determination of the percent rapid recovery of the precursor material. A second sample of 300 mm length was placed into a thinwall stainless steel tube of .21" (0.53 cm) inside diameter and compressed manually achieving a 67% compression. This compression was maintained by use of a plug restraint. The assembly was heated in a gravity-convection air oven to an oven temperature of about 300 °C for 15 minutes while the sample was restrained in its compressed state. The assembly was removed from the oven and allowed to cool to approximately 23 °C.

20 The restraint was removed and the sample was removed from the stainless steel tube. The sample was restretched in the direction of original stretch to approximately its original length by hand and allowed to recover for more than one hour. Percent rapid recovery measurements were made both of control samples and samples processed according to the inventive steps described above. Measurements and calculations were made utilizing the percent rapid recovery as defined in the specification. Results are shown in Table 2.

25

30

35

40

45

50

55

Table 2

Sample	Mean Fibril Length(Micron)	1% of Max Tensile Force (kg)	% Rapid Recovery	Inventive Process Parameters			1% of Max Tensile Force (kg)	Inventive Rod % Rapid Recovery
				% Compression	Oven Temp °C	Time Heated (min)		
Control Rod Inventive	41 --	.29 --	2.0 --	--- 67	-- 300	-- 15	-- .24	--- 6.7

## EXAMPLE 3

REPEATABILITY

5

10 A rapidly recoverable tube (sample 1) from Example 1 was stretched 10 times in order to determine the range of % rapid recovery for a sample that has been exposed to repeated elongations. The sample was placed between the grips of the Instron tensile tester with a grip separation of 150 mm. Crosshead speed was set at 500 mm/min to provide a strain rate of 333% per minute. The Instron machine was programmed to stop its crosshead travel upon achieving .53 kg tensile load similar to that of Example 1, sample 1. The

15 length ( $l_1$ ) of the sample while under the 1% of maximum tensile force was determined by measuring the distance between the grips. Alternatively, length ( $l_1$ ) may be measured from the Instron's chart recorder. When the crosshead stopped, the lower grip of the Instron was released, freeing the sample and allowing it to recover in length. Five seconds after the sample was freed from the lower Instron grip, the actual length  $l_2$  of the sample that had been between the grips of the Instron was measured and recorded. The crosshead was

20 returned to its starting position to again provide a grip separation of 150 mm. The sample was again clamped between the lower grips of the Instron tester at the same point on the sample. Sixty seconds after the first application of tension, 0.53 kg tension was again applied and the entire test was repeated. This was done a total of ten times, with  $l_1$  and  $l_2$  being measured and recorded each time. Percent rapid recovery was calculated as previously defined for each tension application. The results are presented in Table 3.

Table 3

30

Test Run	% Rapid Recovery
1	21.8
2	22.2
3	20.4
4	20.4
5	20.3
6	20.3
7	20.9
8	20.3
9	19.7
10	19.1

35

40

## EXAMPLE 4

FLAT SHEET

50 Flat rectangular sheets of expanded PTFE were obtained by longitudinally slitting a 10 mm inside diameter tube made in the same manner as the precursor tube of Example 1, Sample 1. One of these sheets was retained as control sample for determination of its percent rapid recovery. Referring to Figure 7,

55 a second sample sheet 21 was clamped between two thin stainless steel plates 27 and 29 separated to about 0.9 mm from each other. One end edge 23 of the sample sheet 21 was restrained from moving. The opposite end edge 25 was moved towards the restrained end edge with the use of a stainless steel plate 31 thus compressing the sheet of material in the direction of the fibrils, i.e. in the direction parallel to but opposite to the direction it had been stretched. The material was compressed 83%. The compressed

sample was restrained and the assembly was heated in a gravity convection air oven at a temperature of about 380 °C for about 5 minutes. After removal from the oven, the assembly was allowed to cool to about 23 °C and the sheet sample was removed from between the plates. The sample was restretched in the direction of original stretch to approximately its original length and allowed to recover for more than one hour. The percent rapid recovery was measured and calculated using the formula previously described. Results are both inventive and control samples are shown in Table 4.

10

15

20

25

30

35

40

45

50

55

Table 4

Sample	Thickness (mm)	Mean Fibril Length(Micron)	1% of Max Tensile Force (kg)	% Rapid Recovery	Process Parameters according to the invention			1% of Max Tensile Force (kg)	% Rapid Recovery
					% Compression	Oven Temp °C	Time Heated (min)		
Control	1.0	44	.63	2.0	---	---	---	---	---
Inventive	---	---	---	---	83	380	5	.48	18.4

EXAMPLE 5RAPID RECOVERABLE EXPANDED PTFE TUBESFIBRIL MEASUREMENTS

Sample 1,2,3 and 4 of Example 1 were further evaluated to estimate the amount of bending that was imparted to the fibrils by the rapid recovery process. SEM photos taken at 500X (Figures 8,9,10,11,12 and 13) were made of the wall cross-section of each sample. Figures 8 and 9 are photomicrographs of precursor samples having fibril lengths of 10 micrometers and 30 micrometers respectively. Each sample was prepared by cutting a segment and allowing it to relax for a sufficient amount of time, in this case 24 hours. A relaxed state is where the sample segment is under no tension or compression. Each sample was mounted and maintained in its relaxed state.

SEM photos were taken at magnification levels of 500X. Two important factors in determining the magnification level include resolution and fibril sampling. The photographs taken showed between five and ten complete sequential sets of fibrils.

Photomicrographs were marked with two parallel drawn lines spaced 24mm apart, approximately centred on the photograph and oriented so that the lines were substantially parallel to the direction of the fibrils. Moving from left to right along the top drawn line, internodal distance "H" was determined to be the distance between the node attachment points of the first distinct fibril closest to the drawn line. A distinct fibril is one whose complete length can be visually distinguished. Vertical displacement, a distance "V", was next measured as the perpendicular length from distance "H" to the farthest point on the fibril. If the fibril crossed distance "H" one or more times, the distance "V" was determined to be the sum of the maximum perpendicular "V" measurements. The ratio of V/H was calculated for the fibril. Moving to the right along the drawn line, "V" and "H" measurements were determined for four additional fibrils. The photograph was rotated 180° and the process was repeated for five additional fibrils. Mean values of "V" and "H", and V/H were calculated for all ten fibrils examined. Measurement results are summarised in Table 5.

Table 5

Sample	Fibril Length $\mu$	Precursor Tube			Inventive Tube		
		V( $\mu$ )	H( $\mu$ )	V/H	V( $\mu$ )	H( $\mu$ )	V/H
1	29	1.16	25.5	0.05	4.51	15.8	0.28
2	32	1.08	31.9	0.03	3.37	22.7	0.15
3	39	1.08	31.9	0.03	5.04	24.4	0.21
4	10	1.96	20.3	0.09	3.10	8.32	0.37

Claims

1. A porous shaped article consisting essentially of polytetrafluoroethylene (PTFE), said article having a microstructure of nodes interconnected by fibrils, said article having a rapid recovery of more than about 5.5%.

2. A porous shaped article according to claim 1, wherein substantially all of said fibrils have a bent appearance.

3. An extruded, expanded article, heat treated above its crystalline melt point made of a material consisting essentially of PTFE, said porous PTFE having been subsequently compressed at least 50% in the direction in which rapid recoverable characteristics are desired, restrained and heated.

4. An article as claimed in claim 3 wherein the material was subsequently compressed at least 60%, or 75%, or 90% in the direction of desired rapid recoverable characteristics.

5. A porous PTFE article in the form of a tube with a microstructure of nodes and fibrils wherein:

a) the tube has been compressed to less than 50% of its original length and restrained;

b) the tube has been heated at an elevated temperature for a period of time;

c) said tube has been subsequently cooled; and

d) said tube has been stretched to approximately its original length having a rapid recovery in excess of about 5.5%.

6. An article according to any one of claims 1 to 5 in which said article has a rapid recovery of greater than 6%, or 8%, or 10%, or 15%, or 20%, or 22%, or 25%, or 30% or 50%.

7. An article according to any preceding claim in the shape of a tube having smooth inside and outside surfaces.

8. An article according to claim 7, in which the inside surface and the outside surface differ.

9. An article according to claim 1 which has been formed as a tube and subsequently slit longitudinally and opened to form a sheet.

10. An article according to claim 1 in the form of a sheet, a rod, a film or a filament.

11. An article as claimed in claim 9 or 10 having a rapid recover greater than 5.5%, or 10%, or 20%, or 25%, or 30%, or 50% or 75%.

12. A process for making rapidly recoverable PTFE material comprising extruding a preformed billet of a mixture of coagulated dispersion of PTFE and liquid lubricant, expanding said material after removal of liquid lubricant by stretching said material longitudinally and maintaining said material at a temperature between 35° C and the crystalline melt point during stretching, compressing said extruded and expanded PTFE in the direction of fibrils to reduce its size, restraining said PTFE in its compressed state, and heating said compressed PTFE.

13. A process as claimed in claim 12 wherein said compressed PTFE is heated to a temperature above its crystalline melt point.

14. A process for manufacturing a porous PTFE tube with a microstructure of nodes and fibrils having rapid recovery in excess of about 5.5% comprising the steps of:

a) compressing and restraining said tube to less than about 50% of its original length;

b) heating it at an elevated temperature for a period of time;


c) allowing it to cool; and

d) stretching the tube to approximately its original length.


15. A process as claimed in claim 12 wherein said compressed PTFE is not heated.

16. A porous shaped article according to claim 2 wherein said fibrils have a V/H ratio of at least 0.15.


**FIG. 1**  
**PRIOR ART**



**FIG. 2**




**FIG. 7**






**FIG. 3**  
**PRIOR ART**




←→  
DIRECTION OF EXPANSION

**FIG. 4**




←→  
DIRECTION OF EXPANSION  
←→  
DIRECTION OF COMPRESSION


**FIG. 5**  
**PRIOR ART**




**FIG. 6**







*FIG. 8*



*FIG. 9*



*FIG. 10**FIG. 11*

*FIG. 12**FIG. 13*

⑫

**EUROPEAN PATENT APPLICATION**

⑪ Application number: 88309542.4

⑥ Int. Cl.<sup>4</sup>: **B 29 C 61/00**  
**C 08 J 5/18**  
**// B29K27/18**

⑫ Date of filing: 12.10.88

⑬ Priority: 19.10.87 US 110145 23.09.88 US 248887

⑭ Date of publication of application:  
26.04.89 Bulletin 89/17

⑮ Designated Contracting States:  
AT BE CH DE ES FR GB GR IT LI LU NL SE

⑯ Date of deferred publication of search report:  
18.10.89 Bulletin 89/42

⑰ Applicant: **W.L. GORE & ASSOCIATES, INC.**  
**555 Paper Mill Road P.O. Box 9206**  
**Newark Delaware 19714 (US)**

⑱ Inventor: **House, Wayne D.**  
**Rt. 4 Box 948**  
**Flagstaff AZ 86001 (US)**

**Myers, David J.**  
**HC75 Box 2476**  
**Camp Verde, AZ 86322 (US)**

⑲ Representative: **Taylor, Derek George et al**  
**Mathisen, Macara & Co. The Coach House 6-8 Swakeleys**  
**Road**  
**Ickenham Uxbridge UB10 8BZ (GB)**

⑳ **Rapid recoverable PTFE and a process for its manufacture.**

㉑ This invention relates to porous polytetrafluoroethylene (PTFE) materials having the property of rapid recovery and a process for producing these materials. The microstructure of the porous PTFE material consists of nodes interconnected by fibrils, substantially all of the fibrils having a bent or wavy appearance.

The process comprises extruding a billet of a mixture of coagulated dispersion of PTFE and liquid lubricant, removing the lubricant, stretching the material longitudinally and maintaining it at a temperature between 35°C and the crystalline melt point during stretching, compressing the PTFE in the direction of fibrils to reduce its size, restraining the PTFE in its compressed state, and heating the compressed PTFE.

**EP 0 313 263 A3**



DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A, D	US-A-3 953 566 (R.W. GORE) * Column 21, example 16 *	1, 3, 5, 12	B 29 C 67/20 C 08 J 5/18 // B 29 K 27:18
A	DE-A-2 739 705 (SUMITOMO)		
A	US-A-4 596 837 (K. YAMAMOTO et al.)		
A	EP-A-0 106 496 (W.L. GORE & ASSOCIATES)		
A	US-A-4 110 392 (E. YAMAZAKI)		
A	EP-A-0 155 337 (SUMITOMO)		
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			B 29 C C 08 J
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 24-07-1989	Examiner SZAMOCKI G.J.A.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... & : member of the same patent family, corresponding document	